

Classification		Standards
Type of floorcovering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domesitic 23 Commercial 33 Industrial 42
Technical Characteristics		Standards
Total thickness	EN ISO 24346	Typical value: -1.10-0.13 mm
Wear layer thickness	EN ISO 24340	Typical value: -0.12-0.02 mm
Surface treatment (PUR)		Yes - TopCleanXP™
Beveled edges		Yes - Straight edge
Technical Performances		Standards
Dimensional stability	EN ISO 23999	≤0.12%
Curling resultant to heat	EN ISO 23999	≤1.2 mm
Peeling resistance	EN ISO 24345	≥65 N / 50 mm
Reaction to fire	EN ISO 13501-1	Bs1
Residual indentation	EN ISO 24343-1	≤0.10 mm
Abrasion resistance	EN 660-2	Class T
Scratch resistance		≥2500 g
Impact resistance	EN 13329 Annex F	≥1800 mm
Furniture leg	EN 424	No damage
Castor chair	ISO 4918 / EN 425	No damage
Impact soud redution	EN ISO 717-2	ΔLw = 3dB
Slip resistance	DIN 51130 EN 13893	R 9/R 10 depending on embossing Class DS,μ ≥ 0.45
Thermal resistance	EN ISO 10456	0.02 m²K / W
Light fastness	EN ISO 105-B02	≥ 6
Chemical resistance	EN ISO 26987	Not affected
Electrostatic properties	EN 1815 EN 1081	< 2 kV on concrete >10⁹ Ω
Underfloor heating		Suitable - max. 27 °C